

09/18/00
JCS20 U.S. PTO

09-19-00

A

LYON, P.C
Attorneys & Counselors

Telephone
(248) 645-5200

Suite 207
3883 TELEGRAPH ROAD
BLOOMFIELD HILLS, MICHIGAN 48302-1476

Facsimile
(248) 645-1016

JCS20 U.S. PTO
09/664130
09/18/00

Box Patent Application
Assistant Commissioner for Patents
Washington, D.C. 20231

Attorney Docket No. GIO-004-US

Sir:

Transmitted herewith for filing is the patent application of

Inventor(s): Graylon K. Williams and Sean P. Burns

For: GAS GENERANTS CONTAINING SILICONE FUELS

Enclosed are:

- ☐ 0 sheets of ☐ Formal drawings ☐ Informal drawings.
- ☐ A Declaration and Power of Attorney.
- ☐ A verified statement to establish small entity status under 37 CFR 1.9 and 37 CFR 1.27.
- ☐ A certified copy of a _____ application.
- ☐ An assignment of the invention to _____
- ☒ Certificate of Express Mailing Label No. EL681886624US, Deposited SEPTEMBER 18, 2000

The filing fee has been calculated as shown below:

(Col. 1)		(Col. 2)	SMALL ENTITY		OR	OTHER THAN SMALL ENTITY	
FOR:	NO. FILED	NO.	RATE	FEE		RATE	FEE
BASIC FEE	Xxxxx	Xxxxx	xxxxx	\$ 345		Xxxxx	\$ 690
TOTAL	18	- 20 =	x 9 = \$	0	OR	x 18 = \$	
INDEP.	4	- 3 = 1	x 39 = \$	0	OR	x 78 = \$	78
MULTIPLE DEPENDENT CLAIM(S), IF ANY			+ 135 =	0	OR	+ 270 =	0
			TOTAL:	\$ 0	OR	TOTAL:	\$ 768

*If the difference in Col. 1 is less than zero, enter "0"

- ☐ Please charge my Deposit Account No. 12-2490 in the amount of \$ _____.
- ☒ A check in the amount of \$ 768.00 to cover the filing fee is enclosed.
- ☒ The Commissioner is hereby authorized to charge payment of the following fees associated with this communication or credit any overpayment to Deposit Account No. 12-2490. A duplicate copy of this sheet is enclosed.
- ☒ Any additional filing fees required under 37 CFR 1.16.
- ☒ Any patent application processing fees under 37 CFR 1.17.
- ☒ The Commissioner is hereby authorized to charge payment of the following fees during the pendency of this application or credit any overpayment to Deposit Account No. 12-2490. A duplicate copy of this sheet is enclosed.
- ☒ Any filing fees under 37 CFR 1.16 for presentation of extra claims.
- ☒ Any patent application processing fees under 37 CFR 1.17.
- ☐ The issue fee set in 37 CFR 1.18 at or before mailing of the Notice of Allowance, pursuant to 37 CFR 1.311(b).

9/18/2000
Date

Laurence C. Begin
Laurence C. Begin (Reg. No. 42,310)

GAS GENERANTS CONTAINING SILICONE FUELS
CROSS-REFERENCE TO RELATED APPLICATIONS

This application claims the benefit of U.S. Provisional
5 Application Serial Nos. 60/154,242 and 60/154,293 filed September 16, 1999.

BACKGROUND OF THE INVENTION

Field of the Invention

10 The present invention generally relates to gas generant compositions for inflators of occupant restraint systems. High gas yield gas generants often lose large amounts of heat to the inflator body and surroundings during combustion, and thereby result in a lower generant burn rate and a reduced performance. Compositions provided in accordance with the present invention exhibit a rapid and sustained burn at ambient pressure. Other benefits may
15 include a relatively lower combustion temperature and/or an increase in the moles of gas produced per gram of gas generant composition.

Certain applications incorporating gas generation require a relatively fast burn at ambient pressure, as compared to known nonazide gas generant compositions. Many known nonazide compositions simply cannot sustain a
20 combustion burn rate, adequate for inflation of an airbag for example, under ambient conditions. To overcome this disadvantage, combustion must occur in pressurized conditions. As a result, the combustion vessel (an airbag gas generator for example) must be manufactured to accommodate pressures of 1000 pounds per square inch (psi) or greater. The need to pressurize the
25 combustion vessel during combustion requires a more robust inflator and therefore increases the manufacturing costs.

Certain gas generant compositions or propellants containing silicone and a perchlorate oxidizer (compositions containing silicone and potassium perchlorate, for example) exhibit a relatively rapid burn rate and sustainable
30 combustion at ambient pressure. Nevertheless, to sustain combustion, the

combustion temperature is quite hot. As a result, these compositions are not suitable for certain applications unless an adequate heat sink is also provided. Therefore, the manufacturing cost of the inflator or combustion vessel again increases.

5 Silicone as a fuel is advantageous over other known nonazide fuels known to be useful in occupant restraint systems, for example. Because silicone does not contain nitrogen, undesirable nitrogen oxides are reduced or eliminated as combustion products. Additionally, silicone also provides elasticity to the gas generant composition thereby reducing the propensity for
10 fracture of the gas generant over time. Finally, silicone aids in sustaining combustion at ambient pressure.

 Therefore, a gas generant composition utilizing silicone as a primary fuel and yet exhibiting a rapid and sustained burn rate along with an acceptable combustion temperature would be an improvement in the art.

SUMMARY OF THE INVENTION

20 The above-referenced problems are resolved by gas generant compositions containing silicone as a fuel; an oxidizer selected from the group including metal and nonmetal perchlorates such as potassium perchlorate, lithium perchlorate, and ammonium perchlorate; and, a coolant selected from the group including metal carbonates, metal bicarbonates, metal oxalates, and metal
25 hydroxides. In accordance with the present invention, the addition of a coolant to a composition containing a perchlorate oxidizer and a silicone fuel results in a composition that combusts at rapid and sustained burn rates at ambient pressure. Additionally, the combustion temperature is substantially lower than other state of the art compositions.

30 Preferred gas generant compositions contain coolants having more negative heats of formation. Stated another way, preferred coolants of the


present invention will preferably exhibit a relatively greater negative heat of formation. Accordingly, dissociation of the coolant upon combustion of the gas generant composition results in an endothermic combustion reaction thereby resulting in a cooler combustion temperature. Furthermore, when coolants such as strontium carbonate are employed, strontium silicate is formed thereby forming an insulation around the propellant as it burns. As a result, the heat that is released upon combustion is conserved by the insulating effect of the metal silicate. Although strontium carbonate is the most preferred coolant, other metal salts also exhibit similar characteristics.

DESCRIPTION OF THE PREFERRED EMBODIMENT(S)

In accordance with the present invention, compositions containing at least one silicone polymer (organosiloxane polymers) as a fuel, at least one oxidizer, and at least one coolant component containing a metallic salt and/or base, combust at ambient pressure at acceptable combustion temperatures.


Silicone is defined as any of a large group of siloxane polymers based on a structure consisting of alternate silicon and oxygen atoms with various organic radicals (or functional groups) attached to the silicon. Radicals include, but are not limited by the group including methyl, methoxy, and amino.

The term "silicone" as used herein will be understood in its generic sense. Hawley describes silicone (organosiloxane) as any of a large group of siloxane polymers based on a structure consisting of alternate silicon and oxygen atoms with various organic radicals attached to the silicon:



Formula I: Silicone Example

Or, silicone can be more generically represented as shown in Formula 2:



10 *Formula 2: Silicone Example*

Note, "n" in the Formulas indicates a multiple of the polymeric group or portion of the molecule given within the brackets, to include the organic groups attached to the silicon.

Exemplary silicones include those disclosed in U.S. Patent Nos.
 15 5,589,662, 5,610,444, and 5,700,532, and, in TECHNOLOGY OF POLYMER COMPOUNDS AND ENERGETIC MATERIALS, Fraunhofer-Institut für Chemische Technologie (ICT), 1990, each reference and document herein incorporated by reference.

The compositions of the present invention contain silicone as a fuel. The
 20 fuel component is provided at 10-25% by weight of the gas generant composition.

The gas generant compositions of the present invention contain one or more primary oxidizers selected from the group including metal and
 25 nonmetal perchlorates.

If desired, exemplary secondary oxidizers include but are not limited to phase stabilized ammonium nitrate, ammonium nitrate, potassium nitrate, and strontium nitrate. Stated another way, secondary oxidizers may be selected from the group including metal and nonmetal chlorates, oxides,
 30 nitrates, and nitrites, or other well known oxidizers.

A coolant is selected from the group including metal carbonates,

metal oxalates, metal bicarbonates, and metal hydroxides. "Metal" is defined as alkali, alkaline earth, and transitional metals. Exemplary coolants include but are not limited to strontium carbonate, magnesium carbonate, calcium carbonate, potassium carbonate, strontium oxalate, and magnesium hydroxide.

5 An additional benefit of the coolant is that upon combustion, the resulting metal and silicate ions formed during combustion will form metal silicates. As a result, a coating will form within the combustion chamber and insulate the propellant within the pressure vessel thereby conserving the heat of reaction and contributing to a strong and sustained burn rate at ambient
10 pressure.

Preferred compositions include silicone, a metal perchlorate oxidizer, and an alkaline earth carbonate. A most preferred composition contains silicone, potassium perchlorate, and strontium carbonate. This composition results in the formation of strontium silicates. The substantial
15 negative heat of formation of strontium carbonate results in an endothermic combustion reaction. As a result the combustion temperature is reduced. counters the heat loss that generally results from high gas yield gas generants.

Metal silicates are formed upon combustion of the gas generant compositions containing silicone and metal salts as coolants. Strontium
20 silicates (or other metal silicates) function as ceramic insulators. Therefore, the metal silicates formed upon combustion insulate the propellant chamber thereby maintaining sufficient heat proximate to the burning surface of the propellant and improving combustion characteristics. As such, the heat of combustion is endothermically minimized by the negative heat of formation of
25 the coolant, and is then retained during combustion by the additional insulating benefit.

The gas generant composition contains 10-25% by weight of silicone, 30-85% by weight of a primary oxidizer, and 1-30% by weight of a coolant. If desired, one or more secondary oxidizers are employed at 30-50%
30 by weight of the gas generant composition. The gas generant constituents in similarly sized granular or smaller particulates are added to a tumble blender at

100°C and homogeneously blended, preferably for at least two hours. Silicone is preferably added as a resin that is previously blended with a curing agent. In general, the order in which the constituents are added is not critical so long as they are homogeneously blended. Other known wet and dry blending methods may also be used. Once blending is complete, the gas generant constituents may be extruded or formed into specific shapes such as elongated extrusions, pellets, sheets, or granules.

Table 1 exemplifies the present invention. As shown in the table, compositions consisting of silicone and a perchlorate oxidizer have rapid and sustained burn rates (at 3000 psi) greater than or equal to one inch per second. These combustion properties have been observed at ambient pressure wherein the burn rate is approximately 0.4 inches per second or greater. Nevertheless, the combustion temperatures are relatively high. See Examples 2 and 3. However, when a coolant such as a metal carbonate is added, the temperatures in certain cases are notably reduced. See Examples 17, 21, and 24, for example.

Example	Formulation	Mol gas/100g	Tc @ 3000psi	Density g/cc	Gas Yield %	Comment
1	82% $\text{Sr}(\text{NO}_3)_2$ 18% Silicone	1.6	2100	2.20	45.2	Slow ignition and burning; well-formed slag
2	79% KClO_4 21% Silicone	1.4	3182	1.90	40.8	Rapid and sustained burn at ambient pressure
3	80% KClO_4 20% Silicone	1.4	3130	1.93	43.4	Rapid and sustained burn at ambient pressure
4	31% KClO_4 19% Silicone 50% $\text{Sr}(\text{NO}_3)_2$	1.5	2100	2.08	43.2	Slower ignition and burning than Ex.2 and 3; well-formed slag
5	30% KClO_4 20% Silicone 50% $\text{Sr}(\text{NO}_3)_2$	1.6	2100	2.05	46.7	Slower ignition and burning than Ex.2 and 3; well-formed slag
6	30% LiClO_4 22% Silicone 48% $\text{Sr}(\text{NO}_3)_2$	1.7	2222	1.98	46.7	Slower ignition and burning than Ex.2 and 3; well-formed slag
7	20% LiClO_4 20% Silicone 60% $\text{Sr}(\text{NO}_3)_2$	1.6	2099	2.07	46.4	Slower ignition and burning than Ex.2 and 3; well-formed slag

Example	Formulation	Mol gas/100g	Tc @ 3000psi	Density g/cc	Gas Yield %	Comment
8	29% LiClO ₄ 20% Silicone 40% Sr(NO ₃) ₂ 11% NH ₄ NO ₃	1.9	2207	1.93	52.6	Burn is slower than non-AN* formulas; higher gas yield
9	45% LiClO ₄ 20% Silicone 35% NH ₄ NO ₃	2.6	2923	1.70	65.8	Burn is slower than non-AN formulas; higher gas yield
10	27% LiClO ₄ 20% Silicone 35% Sr(NO ₃) ₂ 18% NH ₄ NO ₃	2.2	2379	1.88	55.9	Burn is slower than non-AN formulas; higher gas yield
11	37% LiClO ₄ 19% Silicone 44% NH ₄ NO ₃	2.8	2841	1.67	69.8	Burn is slower than non-AN formulas; higher gas yield
12	53% KClO ₄ 20% Silicone 27% Sr(NO ₃) ₂	1.5	2594	2.00	42.0	Slower ignition and burning than Ex.2 and 3; well-formed slag
13	27% LiClO ₄ 20% Silicone 36% Sr(NO ₃) ₂ 17% NH ₄ NO ₃	2.0	2000	1.93	55.4	Burn is slower than non-AN formulas; higher gas yield but liberates H ₂ and CO
15	58% LiClO ₄ 20% Silicone 22% Na ₂ CO ₃	1.5	3291	1.90	51.0	Rapid and sustained burn at ambient pressure
16	58% LiClO ₄ 20% Silicone 22% SrCO ₃	1.5	2296	2.00	47.5	Rapid and sustained burn at ambient pressure
17	58% LiClO ₄ 20% Silicone 22% CaCO ₃	1.5	2100	1.95	51.8	Rapid and sustained burn at ambient pressure
18	71% LiClO ₄ 19% Silicone 10% C ₃ H ₆ N ₆	1.9	3161	1.83	56.2	
19	49% KClO ₄ 21% Silicone 30% Sr(NO ₃) ₂	1.5	2633	1.98	41.9	Slower ignition and burning than Ex.2 and 3; well-formed slag
20	20% Silicone 80% NH ₄ NO ₃	3.4	3094	1.64	83.8	Burn is slower than non-AN formulas; higher gas yield but liberates H ₂ , HCl, CO
21	58% LiClO ₄ 20% Silicone 22% CaC ₂ O ₄	1.6	2277	1.86	53.7	Rapid and sustained burn at ambient pressure
22	51% LiClO ₄ 22% Silicone 27% NH ₄ NO ₃	2.4	3007	1.7	61.9	Burn is slower than non-AN formulas; higher gas yield but liberates H ₂ and CO
23	10% KClO ₄ 20% Silicone 70% Sr(NO ₃) ₂	1.6	2100	2.11	55.9	Slower ignition and burning than Ex.2 and 3; well-formed slag
24	60% KClO ₄ 20% Silicone 20% SrCO ₃	1.5	2363	2.03	37.5	Rapid and sustained burn at ambient pressure

Table 1

In general, compositions containing ammonium nitrate and/or other metal nitrates or secondary oxidizers in amounts greater than 50% by weight of the gas generant composition did not exhibit sufficient burn rates (.4 inches per second or greater) at ambient pressure. Strontium salts that are not oxidizers are preferred given the greater cooling effect. Compare Examples 19 and 24.

Furthermore, in accordance with the present invention, certain compositions exhibit relatively higher temperatures than a preferred embodiment containing silicone, strontium carbonate and potassium perchlorate, for example, but still sustained rapid combustion at ambient pressure. As a result, these compositions are still desirable from the perspective that a less robust inflator is required.

Combustion properties may be tailored by adding known ballistic modifiers and catalysts if desired.

The gas generant constituents of the present invention are available from well-known sources such as Fisher Chemical or Aldrich. The silicone polymers may be purchased, for example, from General Electric in Waterford, New York.

The compositions of the present invention are useful in many applications requiring gas generation. These compositions have particular utility as gas generant compositions that may be combusted to inflate an airbag in a vehicle occupant protection system, for example.

While specific embodiments have been described in detail, those with ordinary skill in the art will appreciate that various modifications and alternatives to those details could be developed in light of the overall teachings of the disclosure. Accordingly, the particular arrangements disclosed are meant to be illustrative only and not limiting as to the scope of the invention, which is to be given the full breadth of any claims which are derivable from the description herein, and any and all equivalents thereof.

WE CLAIM:

1. A gas generant composition comprising:
silicone as a fuel;
5 an oxidizer selected from the group consisting of metal and nonmetal perchlorates; and
a coolant selected from the group consisting of alkali, alkaline earth, and transitional metal carbonates, bicarbonates, oxalates, and hydroxides.
10
2. The gas generant composition of claim 1 further comprising:
a secondary oxidizer selected from the group consisting of metal and nonmetal nitrates.
3. The gas generant composition of claim 1 wherein said oxidizer is selected
15 from the group consisting of potassium perchlorate, ammonium perchlorate, and lithium perchlorate.
4. The gas generant composition of claim 1 wherein said composition
20 comprises:
silicone;
potassium perchlorate; and
strontium carbonate.
5. The gas generant composition of claim 1 wherein said composition
25 comprises:
silicone;
potassium perchlorate; and
strontium oxalate.
- 30 6. The gas generant composition of claim 1 wherein said composition comprises:

silicone;
potassium perchlorate; and
calcium oxalate.

- 5 7. The gas generant composition of claim 1 wherein said composition comprises:

silicone;
potassium perchlorate; and
calcium carbonate.

10

8. The gas generant composition of claim 1 wherein said composition comprises:

silicone;
potassium perchlorate; and
magnesium hydroxide.

15

9. The gas generant composition of claim 1 wherein said composition comprises:

silicone;
potassium perchlorate; and
magnesium carbonate.

20

10. The gas generant composition of claim 1 wherein said composition comprises:

silicone;
lithium perchlorate; and
a coolant selected from the group consisting of strontium carbonate,
calcium carbonate, strontium oxalate, magnesium carbonate,
magnesium hydroxide, and potassium carbonate.

25

30

11. A gas generant composition comprising:

silicone at 10-25%;

a primary oxidizer selected from the group consisting of metal and nonmetal perchlorates at 30-85%; and

a coolant selected from the group consisting of alkali, alkaline earth, and transitional metal carbonates, oxalates, bicarbonates, and hydroxides at 1-30%, said percentages stated by weight of said gas generant composition.

12. The gas generant composition of claim 11 further comprising:

at least one secondary oxidizer selected from the group consisting of nonmetal, alkali metal, alkaline earth metal, and transitional metal chlorates, nitrates, nitrites, and oxides at 30-50% by weight of said gas generant composition.

13. The gas generant composition of claim 12 wherein said at least one secondary oxidizer is selected from the group consisting of phase stabilized ammonium nitrate, ammonium nitrate, strontium nitrate, and potassium nitrate.

14. A method of inflating an airbag comprising the step of: combusting a gas generant composition comprising silicone, an oxidizer selected from the group consisting of metal and nonmetal perchlorates, and a coolant selected from the group consisting of metal carbonates, metal oxalates, metal bicarbonates, and metal hydroxides.

15. The method of claim 14 wherein said silicone is provided at 10-25%, said oxidizer at 30-85%, and said coolant at 1-30%, said percentages stated by weight of said gas generant composition.

16. A gas generant composition comprising:

silicone at 10-25%;
potassium perchlorate at 30-85%; and
a coolant selected from the group consisting of alkali metal, alkaline earth
metal, and transitional metal carbonates, oxalates, and hydroxides
at 1-30%, said percentages stated by weight of said gas generant
composition.

17. The gas generant composition of claim 16 comprising:

silicone at 10-25%;
potassium perchlorate at 30-85%; and
strontium carbonate at 1-30%, said percentages stated by weight of said
gas generant composition.

18. The gas generant composition of claim 17 comprising:

silicone at 20%;
potassium perchlorate at 60%; and
strontium carbonate at 20%, said percentages stated by weight of said
gas generant composition.

GAS GENERANTS CONTAINING SILICONE FUELS

ABSTRACT

- 5 Gas generating compositions are provided containing silicone, a metal or nonmetal perchlorate oxidizer, and a coolant selected from the group including metal carbonates, metal bicarbonates, metal oxalates, and metal hydroxides. These compositions exhibit rapid and sustained burn rates at ambient pressure while maintaining acceptable combustion temperatures.